

2021 Bottle Roll Oko Main Zone



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **G2 Goldfields Inc**
141-1101 Adelaide St West
Toronto, Ontario
M5H 3L5 Canada

TEST REPORT:	GUY2110599
---------------------	-------------------

Project Name: 1
 Job Received Date: 05-Nov-2021
 Job Report Date: 03-Dec-2021
 Number of Samples: 7
 Report Version: Final

COMMENTS:

Coarse gold may be present in some samples.

Test results reported relate to the tested samples only on an "as received" basis. Unless otherwise stated above, sufficient sample was received for the methods requested and all samples were received in acceptable condition. Analytical results in unsigned reports marked "provisional" are subject to change, pending final QC review and approval. The customer has not provided any information that can affect the validity of the test results. Please refer to MSALABS' Schedule of Services and Fees for our complete Terms and Conditions. Preliminary results are applicable when a portion of samples in a job is 100% completed and reported or 1 of a number of methods on the same job have been completed 100%. Results cannot change, but additional results or results for additional methods can be added.

SAMPLE PREPARATION	
METHOD CODE	DESCRIPTION
PRP-920-3	Dry, crush 3kg to 2mm, split 1kg & pulverize to 85% -75µm. Guyana spec
	Sample preparation performed by MS Analytical Guyana

ANALYTICAL METHODS	
METHOD CODE	DESCRIPTION
MET-FA1	Au, Fire Assay, 30g fusion, AAS, Trace Level
MET-FA3	Au, Fire Assay, 30g fusion, Gravimetric
Au-CN04	Au, Cyanide Leach at 1000g, AAS

Signature:

Yvette Hsi, BSc.
 Laboratory Manager
 MSALABS



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **G2 Goldfields Inc**
141-1101 Adelaide St West
Toronto, Ontario
M5H 3L5 Canada

TEST REPORT:	GUY2110599
---------------------	-------------------

Project Name: 1
 Job Received Date: 05-Nov-2021
 Job Report Date: 03-Dec-2021
 Report Version: Final

Sample ID	Sample Type	PWE-100 Rec. Wt. kg	Method Analyte Units	MET-FA1 Au ppm	MET-FA3 Au ppm	Au-CN04 Au ppm
		0.01	LOR	0.005	0.9	0.1
Quartz Blank	QC-P-BK	--		<0.005		
Quartz Blank	QC-P-BK	--		<0.005		
21072015	Core	1.75		9.482		7.6
21072016	Core	1.65		3.627		5.0
21077024	Core	2.85		>10	32.1	29.4
21077024PD	QC-PD	--		>10	26.5	28.0
21077058	Core	1.65		>10	680.7	708.4
21081032	Core	1.85		2.510		2.1
C0003368	Core	1.10		>10	53.7	50.9
V5238	Core	2.15		5.240		6.0
21072015-R	Pulp			0.039		
21072016-R	Pulp			0.081		
21077024-R	Pulp			0.134		
21077024PD-R	Pulp			0.137		
21077058-R	Pulp			>10	6.1	
21081032-R	Pulp			0.137		
C0003368-R	Pulp			0.158		
V5238-R	Pulp			0.100		
STD BLANK				<0.005		
STD BLANK					<0.9	
STD BLANK						<0.1
STD OxK160				3.660		
STD OxQ115					25.5	
STD OxK160						3.7

***Please refer to the cover page for comments regarding this test report. ***